

PolyGen 2024 LLDPE



ShawPolymers

Product Description

Linear Low Density Polyethylene – Injection - Housewares / Compounding

Properties	Property Value	Test Method
Melt Index (g/10 min)	20.0	ASTM D1238
Density (g/cm3)	0.924	ASTM D1505
Flexural Modulus (psi)	60,000	ASTM D882
Tensile Strength Yield (psi)	1,100	ASTM D882
Elongation @ Break (%)	60	ASTM D882

* These average values were obtained from specimens molded under carefully controlled laboratory conditions. This data should be used only as a guide and no assurance can be granted by the company that all molded articles will exhibit duplicate properties at those listed above.

The information contained herein is based on our best knowledge and we believe it to be true and accurate. Please read all statements and recommendations in conjunction with our conditions of sale, which apply, to all goods supplied by us. Statements concerning possible uses of materials described wherein are not to be construed as recommendations for use of such materials in the infringement of any patent or copyright. The user of this material must make their own evaluations to determine the suitability of this material from a technical as well as a health, safety and environmental standpoint. This data is not intended for specification purposes.

shawpolymers.com



CORPORATE HEADQUARTERS

400 N. Indiana Ave.
Crown Point, IN 46307