



55B035S.DEV - High-Density Polyethylene Resin

Technical Data Sheet



Product Description

Shell Polymers HDPE 55B035S is a high molecular weight, ethylene-hexene copolymer exhibiting the characteristics of excellent stiffness to ESCR ratio, good impact resistance and durability.



Highlights

- Designed for sheet extrusion applications.

Resin Properties	Method	Nominal Value
Density	ASTM D792	0.955 g/cm ³
Melt Index (190 °C / 2.16 kg)	ASTM D1238	0.35 g/10 min

Mechanical Properties	Method	Nominal Value (English)	Nominal Value (SI)
Environmental Stress-Cracking Resistance (ESCR) ^(a)	ASTM D1693	>35 hr	>35 hr
Tensile ^(b) Strength at Yield	ASTM D638	4100 psi	28.4 MPa
Tensile ^(b) Strength at Break	ASTM D638	2500 psi	17.7 MPa
Tensile ^(b) Elongation at Yield	ASTM D638	9.0%	9.0%
Tensile ^(b) Elongation at Break	ASTM D638	>600%	>600%
Flexural Modulus 1% Secant	ASTM D790B	189,000 psi	1300 MPa
Flexural Modulus 2% Secant	ASTM D790B	160,000 psi	1100 MPa

Thermal Properties	Method	Nominal Value (English)	Nominal Value (SI)
Peak Melting Temperature		270 °F	132 °C
Peak Crystallization Temperature		244 °F	118 °C

Notes:

Typical properties only. Not to be construed as specifications. Users should confirm results by performing their own tests.

Plaques molded in accordance with ASTM D4703C

^(a)Tensile properties tested on Type IV specimens

Regulatory Statement:

- Complies with U.S. FDA 21 CFR 177.1520 (c) 3.1a or 3.2a
- Consult the Regulatory Data Sheet for more details. It is available upon request. Please contact your Account Manager.

www.shell.us/polymers

Legal Disclaimer: All products purchased or supplied by Shell Chemicals are subject to terms and conditions set out in the contract, order acknowledgment and/or bill of lading. Shell Chemicals warrant that their product will meet those specification designates as such herein. All other information, including that herein, supplied by Shell Chemicals is considered accurate but is furnished upon the express condition that the customer shall make its own assessment to determine the products' suitability for a particular purpose. Shell Chemicals make no other warranty either express or implied, regarding such other information, the data upon which the same is based, or the results to be obtained from use thereof; that any products shall be merchantable or fit for any purpose; or that the use of such other information or product will not infringe any patent. Each company should decide based upon their own decision-making process to apply the guidance contained in this document, in full, partly or to adopt other measures, and each company remains responsible for all determinations regarding any use of products, processes or materials described herein and for product and equipment in its possession and control. Specific procedures and requirements must adhere to applicable law and regulatory standards. The expression 'Shell' or 'Shell Polymers' refers to the companies of the Shell Group that are engaged in chemical businesses. Each of the companies that make up the Shell Group of companies is an independent entity and has its own separate identity.

HDTD.55B035S.DEV.R1

